

## Technical Data Sheet – Non-stick coating K 10101

(conducting, for ROEDURTHERM E-300 AS-HT, AS-C and AS-I)

### Description:

K10101 is a tribologically effective coating based on PTFE. The part is thermally or chemically degreased prior to coating. In order to increase the coating bond to subsurface, sandblasting is recommended. After coating the surface of the part is slightly roughened, feels like wax, and has a greyish color. K10101 is characterized by a good wear resistance and was developed especially for high-temperature applications. The product can be applied to plastic and/or all metallic surfaces.

### Physical Properties

Color:	Grey
Layer thickness:	20-30µm
Recommended operating temperature:	Long-term -40 to 260°C
Food authorization:	No, manufactured acc. to EG 2023/2006
Electrostatic discharge capacity:	< 10 <sup>8</sup> Ohm
Anti-sticking properties:	Low
Chemical resistance:	Resistant against water, several mineral oils
Abrasion resistance:	Conditionally resistant
Pencil hardness acc. to DIN EN 13523-4:	HB
Water contact angle:	85
Dynamic sliding friction coefficient:	0,14
Adhesion acc. to DIN EN ISO 2409:	GT0
Mandril bending test DIN EN ISO 1519:	2,5

#### Address

RÖSNICK Vertriebs GmbH  
 Graf-Salm-Straße 34  
 50181 Bedburg  
 Executive Manager  
 Frank Rösnick,  
 Dominik Alferts

#### Contact

**Phone** +49 (0) 2272 - 91 81-70  
**Fax** +49 (0) 2272 - 91 81-90  
**Mail** info@roesnick-vertrieb.de  
**Web** www.roesnick-vertrieb.de

#### VAT No.

DE811738631

#### Commercial register

Cologne HRB 40959

#### Bank details

VR Bank eG, Bergisch Gladbach  
 IBAN: DE57 3706 2600 3646 5360 13, BIC: GENODED1PAF  
 Commerzbank AG, Köln  
 IBAN: DE44 3708 0040 0429 1645 00, BIC: DRESDEFF370

## Technical Data Sheet – Non-stick coating K 10101 (conducting, for ROEDURTHERM E-300 AS-HT, AS-C and AS-I)

### Typical Application Areas:

Soldering frames, soldering masks, coating frames

### Application oriented pilot tests are strictly necessary!

All technical data are based on supplier's data and own examinations and experiences. They are not binding and do not oblige us to any guarantee. They are exclusively intended as information for technicians and application engineers at own risk.

Last updated: 08/2018

#### Address

RÖSNICK Vertriebs GmbH  
Graf-Salm-Straße 34  
50181 Bedburg  
Executive Manager  
Frank Rösnick,  
Dominik Alferts

#### Contact

**Phone** +49 (0) 2272 - 91 81-70  
**Fax** +49 (0) 2272 - 91 81-90  
**Mail** [info@roesnick-vertrieb.de](mailto:info@roesnick-vertrieb.de)  
**Web** [www.roesnick-vertrieb.de](http://www.roesnick-vertrieb.de)

#### VAT No.

DE811738631

#### Commercial register

Cologne HRB 40959

#### Bank details

VR Bank eG, Bergisch Gladbach  
IBAN: DE57 3706 2600 3646 5360 13, BIC: GENODED1PAF  
Commerzbank AG, Köln  
IBAN: DE44 3708 0040 0429 1645 00, BIC: DRESDEFF370