

Technical Information ROEDURTHERM E-300 AS-HT (antistatic base material)

Mechanical Properties	Norm	Unit	Values
Flexural strength	ISO 178	MPa	400
Flexural strength at 150°C / 1h	ISO 178	MPa	250
Modulus of elasticity in flexure, RT	ISO 178	MPa	N/A
Compression strength, RT	ISO 604	MPa	280
Tensile strength	ISO 527	MPa	290

Electrical Properties	Norm	Unit	Values
Surface resistance	IEC 61340-5-1	Ohm	10 ⁵ -10 ¹⁰

Thermic Properties	Norm	Unit	Values
Thermal conductivity	DIN 52612	W/mK	0,3
Coefficient of linear expansion	DIN 53752	1.0E-6/K	15
Temperature Index (TI)	IEC 60216	°C	180

Physical Properties	Norm	Unit	Values
Density	ISO 1183	g/cm ³	1,9
Water absorption 24h 23°C	ISO 62	Mg/%	10/0,03

Thickness	Tolerance to nominal thickness
3-14 mm	According to DIN EN 60893-3-2

Last updated: 2018

Address

RÖSNICK Vertriebs GmbH
Graf-Salm-Straße 34
50181 Bedburg
Executive Manager
Frank Rösnick,
Dominik Alferts

Contact

Phone +49 (0) 2272 - 91 81-70
Fax +49 (0) 2272 - 91 81-90
Mail info@roesnick-vertrieb.de
Web www.roesnick-vertrieb.de

VAT No.

DE811738631

Commercial register

Cologne HRB 40959

Bank details

VR Bank eG, Bergisch Gladbach
IBAN: DE57 3706 2600 3646 5360 13, BIC: GENODED1PAF
Commerzbank AG, Köln
IBAN: DE44 3708 0040 0429 1645 00, BIC: DRESDEFF370